

- 1. Introduction** ALEXSEAL® Finish Primer 442 is an epoxy-based finish primer offering advanced adhesion qualities over various substrates, exceptional sanding characteristics, and an improved film build.
- 2. Range of application** ALEXSEAL® Finish Primer 442 is designed to prime and seal old and new, properly prepared, stable surfaces such as gelcoat and fiberglass, as well as to seal other Alexseal® primers and filler systems. Alexseal® Finish Primer 442 is also designed to cure at cooler temperatures. Using this primer as a base enhances the “Wet Look” of ALEXSEAL®’s Topcoats. Finish Primer 442 may be used above and below the waterline.
- 3. Color** Colors of mixture: White  
Gray
- 4. Coverage** Coverage for ALEXSEAL® Finish Primer 442 when applying 2 - 3 coats or passes in the same application period.
- Volume Solids catalyzed without reduction: 39 %.
- Theoretical:** 4 m<sup>2</sup> / l (168 sq. ft. per gallon) at recommended dry film thickness of 75 - 100 microns (3 - 4 mils).
- Practical:** **Conventional Air Spray Equipment:** 2.4 m<sup>2</sup> / l (100 sq. ft. per gallon) at recommended dry film thickness of 75 - 100 microns (3 - 4 mils).  
**HVLP Air Spray Equipment:** 2.7 m<sup>2</sup> / l (115 sq. ft. per gallon) at recommended dry film thickness of 75 - 100 microns (3 - 4 mils).  
**Brush / Roller and Airless Spray Equipment:** 4 m<sup>2</sup> / (168 sq. ft. per gallon) at recommended dry film thickness of 75 - 100 microns (3 - 4 mils).
- 5. Substrate pre-treatment** The substrate must be clean, dry and free from dust, grease, oil and other contamination.
- Fiberglass and gel coat should be coated directly with ALEXSEAL® Finish Primer 442 after sanding with 100 - 150 grit.
- Refit and repair: Old coatings must have good adhesion and chemical resistance and must be sanded with 100 - 150 grit. A compatibility test should be performed if the old coating is questionable.
- Steel and Aluminum should initially be coated with P1095 ALEXSEAL® Protective Primer 101.
- Fairing Systems: ALEXSEAL® Finish Primer 442 should be applied over ALEXSEAL® Super Build 302 after block sanding with 100 - 150 grit.
- 6. Trade names**
- |               |       |   |
|---------------|-------|---|
| Base Material | P4420 | ALEXSEAL® Finish Primer 442, White      |
|               | P4423 | ALEXSEAL® Finish Primer 442, Dark Gray  |
| Converter     | C4427 | ALEXSEAL® Finish Primer 442 Converter   |
| Reducer       | R4042 | ALEXSEAL® Epoxy Primer Reducer          |
| Accelerator   | A4429 | ALEXSEAL® Accelerator Finish Primer 442 |
- 7. Mixing ratio**
- |                             |   |
|-----------------------------|---|
| 1 parts by volume           | ALEXSEAL® Finish Primer 442 Base            |
| 1 part by volume            | C4427 ALEXSEAL® Finish Primer 442 Converter |
| 10 to 25 % reduction (vol.) | R4042 ALEXSEAL® Epoxy Primer Reducer        |
|                             | R5015 ALEXSEAL® Topcoat Reducer Brush       |
- Allow a 15 minute induction period after mixing base and converter, add reducer and remix.  
Example: 1 : 1 : 1/2 = 25 % reduction for spray application

# Finish Primer 442

Technical Data Sheet: 153-40  
**P4420 / P4423**

## 8. Application

Viscosity (Zahn #2)	approx. 25 sec
Fluid Nozzle Size	1.2 to 1.6 mm (0.046 to 0.060) - Conventional & HVLP
Atomizing Pressure	3.0 to 5.0 bar (42 to 70 PSI) - Conventional & HVLP
Pot Pressure	0.7 to 1.5 bar (10 to 20 PSI) - Conventional & HVLP
Airless Equipment	Tip 0.35 - 60 to 0.43 - 60 mm (0.014 - 60 to 0.017 - 60)
Airless Equipment	Pressure 3.0 to 5.0 bar (42 to 70 PSI)

### Spray & Brush

Apply 2 or 3 coats to a wet film thickness (WFT) of 75 - 100 microns (3 - 4 mils) per coat. This will achieve a dry film thickness (DFT) of 100 - 150 microns (4 - 6 mils) for a 2 coat application. Minimum recommended film thickness before sanding is 75 microns (3 mils) DFT. Maximum recommended film thickness during a spray application is 3 coats totaling 300 microns (12 mils) WFT, or 175 microns (7 mils) DFT.

### Accelerator

A4429 ALEXSEAL® Accelerator Finish Primer 442 is used to reduce the drying time of ALEXSEAL® Finish Primer 442. At the same time, use of A4429 ALEXSEAL® Accelerator Finish Primer 442 reduces the pot life. Additional quantities are not recommended.

Add up to 12.5% of A4429 to the catalyzed 442 epoxy primer, or 1 pint A4429 for each mixed gallon of base and converter. A4429 also replaces that amount of the reducer.

Mixing to achieve 12.5% reduction using A4429 is 2 quarts base, 2 quarts converter, 1 pint A4429. Example 1:1:1/4.

Mixing for 25% overall reduction using this accelerator will require 12.5% reduction using A4429 and 12.5% reduction using R4042 Epoxy Primer Reducer. Example 1:1:1/4:1/4.

## 9. Pot life and Drying

Temperature for minimum recoat time	15°C (60°F)	20°C (68°F)	25°C (77°F)	30°C (85°F)	Max Dry Time
Pot Life - approx.	12 hrs	12 hrs	12 hrs	12 hrs	N/A
Pot Life - with A4429 ALEXSEAL® Accelerator Finish Primer 442	6 hrs	6 hrs	6 hrs	6 hrs	N/A
Dust Free	90 min	60 min	45 min	30 min	N/A
Tape Dry - without accelerator	30 hrs	24 hrs	18 hrs	14 hrs	N/A
Tape Dry - with A4429 ALEXSEAL® Accelerator Finish Primer 442	24 hrs	18 hrs	12 hrs	14 hrs	N/A
Fully Cured - without accelerator	11 days	9 days	7 days	5 days	N/A
Recoat with another coat of ALEXSEAL® Finish Primer 442	3 hrs minimum	2 hrs minimum	1 hr minimum	1 hr minimum	24 hrs maximum
Overcoat with another product including 302, and 501. Sanding is required after max time.	12 hrs minimum	12 hrs minimum	12 hrs minimum	12 hrs minimum	24 hrs maximum

Note: The above chart reflects approximate minimum and maximum time. Surface temperature, air flow, direct or non-direct sunlight, quantity of reducer, and film thickness will effect actual times during application. During the drying phase the minimum temperature is 15°C (60°F). Ideal temperature: 25°C (77°F).

## 10. Packaging

P4420	ALEXSEAL® Finish Primer 442, White	1 QT & 1 Gal
P4423	ALEXSEAL® Finish Primer 442, Dark Gray	1 QT & 1 Gal
C4427	ALEXSEAL® Finish Primer 442, Converter	1 QT & 1 Gal
R4042	ALEXSEAL® Epoxy Primer Reducer	1 QT & 1 Gal
A4429	ALEXSEAL® Accelerator Finish Primer 442	1 PT

**Professional Use Only**

**Page 2 of 2**

The information contained in this data sheet is based on our level of research and development. Revisal by the user with regard to the intended aim is necessary due to the diverse processing and application possibilities. revision January 2008