

Spray Fair 328

Technical Data Sheet: 153-30
P3280

1. Introduction

ALEXSEAL® Spray Fair 328 is an epoxy-based, sprayable filler surfacer, which provides the ideal product for yachts that require filling and fairing.

ALEXSEAL® Spray Fair 328 has excellent application, sanding and anti-sagging properties. It is designed to be easy to mix and apply, while the cured film provides an excellent surface for re-coating with other ALEXSEAL® products.

2. Range of application

ALEXSEAL® Spray Fair 328 is used for fairing all appropriately prepared surfaces and can be used for surfaces above the waterline only.

3. Color

Color of mixture: Tan
Base material: Tan
Converter: Yellow

4. Coverage

Volume Solids catalyzed without reduction: 71 %

Note: Coverage rates are figured for base and converter. Reducer is added as percent of total quantity of base & converter.

	m ² / liter	m ² / gal	sq. ft. / gal	@ DFT in μm (mils)
Theoretical	0,6	2,1	23	900 (36)
Practical				
Conventional Air Spray Equipment	0,5	2,0	22	900 (36)
HVLP Air Spray Equipment	0,6	2,4	26	900 (36)
Airless Equipment	0,7	2,8	30	900 (36)

5. Substrate pre-treatment

The substrate must be clean, dry and free from dust, grease, oil and other contamination.

To ensure optimum adhesion, the substrate must be ground and /or blasted with (36 to 60 grit) before priming to ensure system adhesion. Full fairing systems require a heavily abraded substrate. Thin fairing systems of less than 3 mm (1/8 - 0.012 inch) will require a less aggressive profile to anchor the system. Priming is required on most substrates before application of ALEXSEAL® Spray Fair 328.

For metal substrates - optimum mechanical and corrosion resistance values are achieved by proper surface preparation and substrate priming with an ALEXSEAL® Metal Primer.

For GRP substrate, use ALEXSEAL® Finish Primer 442 or Super Build 302. The ALEXSEAL® Primer should be sanded with 60 - 80 grit, after overnight dry, before application of ALEXSEAL® Spray Fair 328.

For custom applications over substrates including epoxy resins, contact your ALEXSEAL® representative.

6. Trade names

Base Material	P3280	ALEXSEAL® Spray Fair 328
Converter	C3287	ALEXSEAL® Spray Fair 328 Converter
Reducer	R3040	ALEXSEAL® High Build Epoxy Reducer

7. Mixing ratio

1 part by volume	P3280	ALEXSEAL® Spray Fair 328
1 part by volume	C3287	ALEXSEAL® Spray Fair 328 Converter
10 - 25 % reduction (vol.)	R3040	ALEXSEAL® High Build Epoxy Reducer

Example: 1 : 1 : 1/4 = 12.5% reduction
Example: 1 : 1 : 1/2 = 25% reduction

Allow a 15 minute induction period after mixing base and converter, add reducer and remix.

The amount of reducer required may vary depending on the application conditions.

Professional Use Only

Page 1 of 2

The information contained in this data sheet is based on our level of research and development. Revisal by the user with regard to the intended aim is necessary due to the diverse processing and application possibilities. revision January 2011

Spray Fair 328

Technical Data Sheet: 153-30
P3280

8. Application

Note: Thick viscosity requires the use of a large nozzle and a pressure pot.
 Fluid Nozzle Size Pressure Pot 2.2 - 2.8 mm (0.08 -0.110 inch) - Conventional & HVLP
 Atomizing Pressure 3.0 to 5.0 bar (44 to 73 PSI) - Conventional & HVLP
 Pot Pressure 1 to 1.5 bar (15 to 22 PSI) - Conventional & HVLP
 Airless Equipment Tip 0.50mm / 60° to 0.60mm / 60° (0.020 / 60° to 0.024 / 60°)
 Inlet Pressure 3 – 5 bar (44 to 70 PSI)

The components of ALEXSEAL® Spray Fair 328 have different colors to ensure thorough mixing. After mixing, the color of the material should be a homogeneous tan color. If they are not mixed thoroughly, it could result in an improperly cured batch. Mixing can be done mechanically with a slow turning dough mixer or manually. The mixing in of air bubbles should be avoided.

Application by Spraying

Apply 3 coats to a wet film thickness (WFT) of 400 - 500 microns (16 - 20 mils) per coat. This will achieve a dry film thickness (DFT) of 700 - 900 microns (28 - 36 mils) for a 3 coat application, using up to 25 % reduction. Maximum dry film thickness per coat is 500 microns (20 mils). Maximum recommended film thickness during a spray application is 3 coats totaling 1500 microns (60 mils) WFT, or 900 microns (36 mils) DFT. Do not apply more than 3 coats without allowing to cure overnight and sanding the surface.

ALEXSEAL® Spray Fair 328 should be block sanded with 80 - 120 grit. Block sanding with 120 grit or finer will help prevent sand scratch print through in the finished system.

Note: This is a solvent based sprayable fairing compound. Solvent entrapment can be caused by heavy film thickness when over coating too quickly with the same product or other products, and by low temperature or slow drying time. Mankiewicz Gebr. & Co. will not accept liability for any damages.

9. Pot life and Drying

Optimal application environment range - min. 15°C (60°F) 40% RH, up to max. 30°C (85°F) 80% RH

Temperature for minimum time	15°C (60°F)	20°C (68°F)	25°C (77°F)	30°C (85°F)	Max Time
Pot Life	8 hrs	8 hrs	8 hrs	8 hrs	8 hrs
Dry to sand	3 - 4 days	2 days	1 day	1 day	N/A
Fully cured	2 weeks	1 week	5 days	4 days	N/A
Recoat after tack up with additional ALEXSEAL® Spray Fair 328	4 hrs	2 hrs	1 hrs	1 hrs	24 hrs

Note: The above chart reflects approximate minimum and maximum time. Surface temperature, air flow, direct or non-direct sunlight, quantity and or choice of reducer, and film thickness will effect actual tack up, recoat, overcoat, and drying times during application. During the drying phase the minimum temperature is 15°C (60°F). Ideal temperature: 25°C (77°F). The minimum application condition should be 3°C (5.4°F) above dew point.

Recoating of ALEXSEAL® Spray Fair 328 over itself within the recommended times above is important to avoid trapping of solvents. Trapped solvents will cause blistering and splitting of this coating as well as retarding the time to sand. Max 3 coats in one application, sand after 24 hrs dry before additional application. ALEXSEAL® Spray Fair 328 is porous. It must be sealed with ALEXSEAL® Super Build 302 or High Build 357 before applying a final primer or topcoat. ALEXSEAL® Super Build 302 or High Build 357 can be applied after the surface has been fully cured and block sanded with 80 to 120 grit. Finishing the fairing by block sanding with 80-120 grit or finer will help prevent sand scratch print through in the final finish.

10. Packaging

P3280	ALEXSEAL® Spray Fair 328	1 Gal
C3287	ALEXSEAL® Spray Fair 328 Converter	1 Gal
R3040	ALEXSEAL® High Build Epoxy Reducer	1 QT & 1 Gal

Professional Use Only

Page 2 of 2

The information contained in this data sheet is based on our level of research and development. Revisal by the user with regard to the intended aim is necessary due to the diverse processing and application possibilities. revision January 2011