

Waterborne Topcoat

Technical Data Sheet: 341-26
W series

- 1. Introduction** ALEXSEAL Waterborne Topcoat is a water reducible two component paint based on polyurethane technology. After curing, the material is characterized by a high gloss retention and color resistance even under extreme climatic conditions. Moreover, the cured film is resistant to abrasion, scratching, solvents, chemicals, synthetic cooling agents and hydraulic oils.
- 2. Range of application** ALEXSEAL Waterborne Topcoat is used in engine rooms and lockers for example. The material should not be used directly on the engines as the heat may cause gloss and color changes. However, this does not affect the film's protective properties.
- 3. Color** ALEXSEAL Waterborne Topcoat is available in white standard factory packaged only.
- 4. Coverage** Volume Solids catalyzed without reduction: 46 %. Coverage for ALEXSEAL Waterborne Topcoat when applying 2 coats.
Note: Coverage rates are figured for base and converter. Reducer is added as percent of total quantity of base & converter.

	m ² / liter	m ² / gal	sq. ft. / gal	Rec. DFT in µm (mils)
Theoretical / Brush and Roller	12	45	484	40 - 50 (2)
Practical				
Conventional Air Spray Equipment	7.2	27.2	293	40 - 50 (2)
HVLP Air Spray Equipment	8.4	31.7	342	40 - 50 (2)

- 5. Substrate pre-treatment** The substrate must be clean, dry and free from dust and grease. Due to its good adhesion properties ALEXSEAL Waterborne Topcoat may be applied directly to fiberglass.
- 6. Trade names & Packaging**
- | | | |
|-------|--|-------|
| W.... | ALEXSEAL Waterborne Topcoat (Base Color) | 1 Gal |
| C9929 | ALEXSEAL Waterborne Topcoat Converter | 1 QT |
- 7. Mixing ratio**
- Spray: 4 parts by volume W.... ALEXSEAL Waterborne Topcoat (Base Color)
1 part by volume C9929 ALEXSEAL Waterborne Topcoat Converter
10 - 15 % by volume Distilled Water
Example: 4 : 1 : 1/2 to 3/4 = 20 % reduction
- Brush / Rolling: 4 parts by volume W.... ALEXSEAL Waterborne Topcoat (Base Color)
1 part by volume C9929 ALEXSEAL Waterborne Topcoat Converter
5 - 10 % by volume Distilled Water
Example: 4 : 1 : 1/4 up to 1/2 = 5 - 10 % reduction

The amount of reducer required may vary depending on the application conditions.

Mixed material must be filtered before application.

Mix ALEXSEAL Waterborne Topcoat Base and ALEXSEAL Waterborne Topcoat Converter with a high-speed mixer for approximately 2 minutes. After this, adjust the application viscosity by adding water.

- 8. Application**
- | | |
|--------------------------------|--|
| Viscosity | Zahn #2: ≈ 37 - 50 sec, DIN 4 cup 4mm: ≈ 30 - 40 sec |
| Nozzle Size Gravity Gun | 1.0 to 1.4 mm (0.040 to 0.050) - Conventional & HVLP |
| Nozzle Size Siphon Cup | 1.2 to 1.6 mm (0.046 to 0.060) - Conventional & HVLP |
| Fluid Nozzle Size Pressure Pot | 1.0 to 1.2 mm (0.040 to 0.042) - Conventional & HVLP |
| Atomizing Pressure | 3.0 to 3.5 bar (42 to 50 PSI) - Conventional & HVLP |
| Pot Pressure | 0.7 to 1.5 bar (10 to 20 PSI) - Conventional & HVLP |

Professional Use Only

Page 1 of 2

The information contained in this data sheet is based on our level of research and development. Revisal by the user with regard to the intended aim is necessary due to the diverse processing and application possibilities. Any liability on part of Mankiewicz for faulty applications and / or improper use is expressly excluded. The processing of the product must be fully documented by means of a paint application protocol. Revision 2023

Waterborne Topcoat

Technical Data Sheet: 341-26
W series

Application by Spraying: Apply 2 coats to a wet film thickness (WFT) of 30 - 40 microns (1.1 – 1.6 mils) per coat. Allow 60 minutes flash time between coats. This will achieve a dry film thickness (DFT) of 30 - 40 microns (1.2 - 1.6 mils) for a 2 coat application. Maximum recommended film thickness during a spray application is 2 coats totalling 60 - 80 microns (2.5 - 3 mils) WFT, or 30 - 40 microns (1.2 - 1.6 mils) DFT.

Application by Brush / Roller: Apply 2 coats to a wet film thickness (WFT) of 30 - 40 microns (1.1 – 1.6 mils) per coat. Each coat should dry to a tape dry stage, 12 - 24 hrs. Sand with 320 - 400 between coats. This will achieve a dry film thickness (DFT) of 30 - 40 microns (1.2 - 1.6 mils) for a 2 coat application. Maximum recommended film thickness during an application is 2 coats totalling 60 - 80 microns (2.5 - 3 mils) WFT, or 30 - 40 microns (1.2 - 1.6 mils) DFT.

9. Pot life and Drying Optimal application environment range - min. 15°C (60°F) 40% RH, up to max. 30°C (85°F) 80% RH

Temperature for minimum time	15°C (60°F)	20°C (68°F)	25°C (77°F)	30°C (85°F)	Max Time
Pot Life - approx.	2 - 3 hrs	2 - 3 hrs	2 hrs	1 ½ hrs	N/A
Dust Free (at 60 % relative humidity)	4 hrs	3 hrs	2 hrs	1 hr	N/A
Tape Dry	26 hrs	24 hrs	18 hrs	12 hrs	N/A
Fully Cured	21 days	18 days	14 days	12 days	N/A
Recoat after tack up with ALEXSEAL Waterborne Topcoat	90 min	60 min	60 min	60 min	24 hrs
Overcoat with another product. Preparation including sanding is required	24 hrs	24 hrs	18 hrs	12 hrs	N/A

Note: The above chart reflects approximate minimum and maximum time. Surface temperature, air flow, direct or non-direct sunlight, quantity of reducer, and film thickness will affect actual times during application. During the drying phase the minimum temperature is 15°C (60°F). Ideal temperature: 25°C (77°F). The minimum application condition should be 3°C (5.4°F) above dew point.

The information contained in this data sheet is based on our level of research and development. Revisal by the user with regard to the intended aim is necessary due to the diverse processing and application possibilities. Any liability on part of Mankiewicz for faulty applications and / or improper use is expressly excluded. The processing of the product must be fully documented by means of a paint application protocol. Revision 2023